with ECOSE® Technology

Submittal Date



Acoustical Performance

Knauf Insulation EcoBatt® Commercial Building Insulation with ECOSE® Technology provides excellent acoustical properties and will reduce sound transmission when properly installed in partition walls and acoustical ceiling and floor systems. Knauf Insulation EcoBatt Acoustical/Thermal Insulation can improve STC ratings in wood stud construc-

tion by 3 to 5 points and metal stud construction by 8 to 10 points depending upon the complexity of the wall configurations, R-values and layers of insulation.

The following table illustrates the improved STC Ratings using Knauf Insulation EcoBatt Acoustical/Thermal insulation compared to no insulation.

STC Ratings*					
	EcoBatt	No insulation	EcoBatt	No insulation	
Wood Frame (3½" - 4" Batt)	(with ½" gypsum	wallboard both sides)	(with 5/8" gypsum wallboard both sides)		
Single studs/Single layer gypsum	38	35	38	34	
Single studs/Resilient channel	47	39	52	40	
Staggered studs/Single layer gypsum	49	39	51**	43	
Double stud walls/Single layer gypsum	57	46	56	45	
Steel Frame (2½" Studs) (2½" - 2¾" Batt)	(with ½" gypsum	wallboard both sides)	(with 5/8" gypsum wallboard both sides)		
Single layer gypsum	45	36	47	39	
Double layer gypsum one side/ Single layer gypsum other side	50	39	52	44	
Double layer both sides	54	45	57	48	
Steel Frame (35/8 " Studs) (31/2" - 4" Batt)	(with ½" gypsum	wallboard both sides)	(with 5/8" gypsum wallboard both sides)		
Single layer gypsum	47	39	50	39	
Double layer gypsum one side/ Single layer gypsum other side	52	42	55	47	
Double layer both sides	56	50	58	52	

^{*} See NAIMA publication BI405 for additional information.

Thermal Resistance

Thermal resistance (R-value) of the blanket insulation only is certified to be as represented above when measured at a mean temperature of 75°F (24°C) and subject to manufacturing and testing tolerances.

Surface Burning Characteristics

Knauf Insulation Unfaced Batts and Blankets, FSK-25 Batts, Insulation Board, Wall and Ceiling Liner M and Black Acoustical Board do not exceed 25 Flame Spread and 50 Smoke Developed when tested in accordance with ASTM E-84.

Fire Safety

Knauf Insulation Unfaced Batts are considered noncombustible according to ASTM E-136. Facings and coated products do affect fire safety and burning characteristics. Please consult your Knauf Insulation sales representative or technical support for additional information and appropriate applications.

Additional Information

MSDS sheets are available on our Web site or by contacting technical support.

All Knauf Insulation products have a one-year limited warranty.

Ask your Knauf Insulation sales representative for the following:

Limited One-Year Warranty Card	K-WC
EcoBatt® QuietTherm® Insulation Data Sheet	BI-BTQ-DS
Insulation Board Data Sheet	BI-IB-DS
Theater Insulation* Products Data Sheet	BI-AC-DS

^{*}Wall and Ceiling Liner M, Black Acoustical Board, Insulation Board

ECOSE® Technology

ECOSE Technology is a revolutionary binder chemistry that makes Knauf Insulation products even more sustainable than ever. It features rapidly renewable bio-based materials rather than non-renewable petroleum-based chemicals traditionally used in fiber glass insulation products. ECOSE Technology reduces binder embodied energy and does not contain phenol, formaldehyde, acrylics or artificial colors.

Fiber Glass and Mold

Fiber glass (glasswool) insulation will not sustain mold growth. However, mold can grow on almost any material when it becomes wet and contaminated. Carefully inspect any insulation that has been exposed to water. If it shows any sign of mold it must be discarded. If the material is wet but shows no evidence of mold, it should be dried rapidly and thoroughly. If it shows signs of facing degradation from wetting, it should be replaced.





GREENGUARD Gold

Knauf Insulation's Batts, Blankets and Insulation Boards have achieved GREENGUARD Gold Certification and are verified to be formaldehyde free.

GREENGUARD Certification Program

Products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg.

Knauf Insulation has achieved a UL Environment claim validation for over 50% post-consumer recycled glass content in our insulation products.





^{**} Uses 2" - 21/2" Batts

with ECOSE® Technology



Submittal Date			
Submitted to:			
Job Name:			
Job Reference:			
Submitted by:			
Address		_ State:	Zip:
E-Mail Address			
Phone:	Fax #:		

Notes

Knauf Insulation is registered to ISO 9001:2008 in the prevention, detection and correction of problems in production and service areas. The chemical and physical properties of Knauf Insulation products with ECOSE Technology—Unfaced Batts and Blankets, FSK-25 Batts, Insulation Board, Wall and Ceiling Liner M and Black Acoustical Board—represent typical average values determined in accordance with accepted test methods. The data is subject to normal manufacturing variations. The data is supplied as a technical service and is subject to change without notice. References to numerical flame spread ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions

Check with your Knauf Insulation sales representative to assure information is current.



with ECOSE® Technology

Submittal Date _____



Knauf Insulation EcoBatt® Commercial Batt	Insulation	n with ECOSE	® Technolog	у	
Product and Description	R-Value/RSI Thickness			ness	Location
☐ Unfaced Thermal and Acoustical					
Glasswool insulation designed to be friction fit between metal framing members. Specifier permitted choice of warm side vapor retarders, including	□ R-8	RSI-1.4	21/2"	64 mm	
	□ R-11	RSI-1.9	3½"	89 mm	
foil backed gypsum board or polyethylene film.	□ R-13	RSI-2.3	3½"	89 mm	
Unfaced glasswool insulation is also an excellent	□ R-19	RSI-3.3	61/4"	159 mm	
sound control insulation, designed for installation in partition walls and as a lay-in over acoustical	□ R-25	RSI-4.4	8"	203 mm	
ceiling panels.	□ R-26	RSI-4.6	9"	229 mm	
When tested in accordance with ASTM E 84, material has Fire Hazard Classification of 25/50 or less	□ R-30	RSI-5.3	10"	254 mm	
Specification Compliance	□ R-38	RSI-6.7	12"	311 mm	
· ·	□ R-49	RSI-8.6	133/4"	349 mm	
 ASTM C 665; Type I, Class A HH-I-521F; Type I, Class A ASTM E 136 					
☐ Kraft Faced Thermal and Acoustical					
Glasswool insulation with kraft paper with flanges.	□ R-11	RSI-1.9	3½"	89 mm	
Kraft vapor retarder has vapor transmission (permeance) rating of 1.0 or less.	□ R-13	RSI-2.3	3½"	89 mm	
Kraft faced glasswool insulation is also an excellent	□ R-19	RSI-3.3	61/4"	159 mm	
sound control insulation, designed for installation in partition walls and as a lay-in over acoustical	□ R-25	RSI-4.4	8"	203 mm	
ceiling panels.	□ R-26	RSI-4.6	9"	229 mm	
Kraft facing will burn and should not be left ex-	□ R-30	RSI-5.3	10"	254 mm	
posed. Install kraft facing in contact with approved finish material.	□ R-38	RSI-6.7	12"	311 mm	
Specification Compliance	□ R-49	RSI-8.6	133/4"	349 mm	
ASTM C 665; Type II, Class C HH-I-521F; Type II, Class C					
☐ FSK-25 Foil Faced					
Glasswool insulation with a flanged reinforced foil/ scrim/kraft facing with an average vapor transmis-	□ R-11	RSI-1.9	3½"	89 mm	
sion (permeance) rating of .04.	□ R-13	RSI-2.3	3½"	89 mm	
When tested in accordance with ASTM E 84, mate-	□ R-19	RSI-3.3	6¼"	159 mm	
rial has Fire Hazard Classification of 25/50 or less.	□ R-30	RSI-5.3	10"	254 mm	
Specification Compliance	□ R-38	RSI-6.7	12"	311 mm	
ASTM C 665; Type III, Class A HH-I-521F; Type III, Class A					
☐ Foil Faced					
Glasswool foil insulation with asphalt-coated	□ R-11	RSI-1.9	3½"	89 mm	
kraft/foil facing with flanges. Foil vapor retarder has vapor transmission (permeance) rating of .05	□ R-13	RSI-2.3	3½"	89 mm	
or less.	□ R-19	RSI-3.3	61/4"	159 mm	
Insulation should not be left exposed. Install foil facing in contact with approved finish material.	□ R-30	RSI-5.3	10"	254 mm	
Specification Compliance	□ R-38	RSI-6.7	12"	311 mm	
ASTM C 665; Type III, Class B HH-I-521F; Type III, Class B					

with ECOSE® Technology

Subn	nittal	Date	
30011	mu	Duie	



Knauf Insulation Black Acoustical Insulation	n with ECOSE	® Technology			
Product and Description	Density		Thickness		Location
☐ Wall and Ceiling Liner M					
Black insulation blanket with a black mat facing	□ 1.0 pcf	16 kg/m³	1"	25 mm	
adhered to one surface. The product is designed for use as an acoustical and visual barrier for walls	□ 1.0 pcf	16 kg/m³	1½"	38 mm	
and ceilings.	□ 1.0 pcf	16 kg/m³	2"	51 mm	
When tested in accordance with ASTM E 84, material has Fire Hazard Classification of 25/50 or less. Specification Compliance ASTM C 553; Types I, II, III • ASTM C 1071; Type I	□ 1.5 pcf	24 kg/m³	1/2"	13 mm	
	□ 1.5 pcf	24 kg/m³	1"	25 mm	
	□ 1.5 pcf	24 kg/m³	1½"	38 mm	
	□ 1.5 pcf	24 kg/m³	2"	51 mm	
	□ 2.0 pcf	32 kg/m³	1/2"	13 mm	
	□ 2.0 pcf	32 kg/m³	1"	25 mm	
☐ Black Acoustical Board					
Black Acoustical Board with a black mat facing adhered to one surface. The product is designed for use as an acoustical and visual barrier for walls and ceilings, where system design requires a rigid product and where additional strength and abuse	□ 2.25 pcf	36 kg/m³	2"	51mm	
	□ 3.0 pcf	48 kg/m³	1½"	38 mm	
	□ 3.0 pcf	48 kg/m³	2"	51mm	

When tested in accordance with ASTM E84, materail has Fire Hazard Classification of 25/50 or less

Specification Compliance

• ASTM C 1071; Type II

Knauf Insulation Insulation Board with ECOSE® Technology							
Product and Description	Density	Thickness		R-Value/RSI		Location	
☐ Insulation Board							
Fiber glass insulation designed to be used on metal		□ 1½"	38 mm	R-6.3	RSI-1.1		
and masonry walls, walls and roof panel systems, curtain wall assemblies, cavity walls and for all ap-		□ 2"	51 mm	R-8.3	RSI-1.5		
plications where insulating and acoustical efficiency is required. It is available plain, with a factory	1.6 pcf	□ 2½"	64 mm	R-10.4	RSI-1.8		
applied foil/scrim/kraft facing or with a factory	26 kg/m ³	□ 3"	76 mm	R-12.5	RSI-2.2		
applied all service jacket.		□ 3½"	89 mm	R-14.6	RSI-2.6		
When tested in accordance with ASTM E 84, material has Fire Hazard Classification of 25/50 or less.		□ 4"	102 mm	R-16.7	RSI-2.9		
, , , , , , , , , , , , , , , , , , ,		□ 1"	25 mm	R-4.3	RSI-0.8		
Specification Compliance	2.25 pcf 36 kg/m³	□ 1½"	38 mm	R-6.5	RSI-1.1		
• HH-I-558B – Form A, Class 1		□ 2"	51 mm	R-8.7	RSI-1.5		
(1.6pcf, 2.25pcf, 3.0 pcf, 4.25pcf, 6.0pcf)		□ 2½"	64 mm	R-10.9	RSI-1.9		
– Form A, Class 2 (3.0pcf, 4.25pcf, 6.0pcf)		□ 3"	76 mm	R-13.0	RSI-2.3		
• HH-B-100B		□ 3½"	89 mm	R-15.2	RSI-2.7		
- Type I (ASJ) - Type II (FSK)		□ 4"	102 mm	R-17.4	RSI-3.1		
• ASTM C 1136		□ l"	25 mm	R-4.3	RSI-0.8		
– Type I, II, III, IV (ASJ)		□ 1½"	38 mm	R-6.5	RSI-1.1		
– Type II, IV (FSK)	0.0	□ 2"	51 mm	R-8.7	RSI-1.5		
• ASTM C 612 - Type IA (1.6pcf, 2.25pcf, 3.0pcf, 4.25pcf,	3.0 pcf 48 kg/m³	□ 2½"	64 mm	R-10.9	RSI-1.9		
6.0pcf)		□ 3"	76 mm	R-13.0	RSI-2.3		
- Type IB (3.0pcf, 4.25pcf, 6.0pcf)		□ 3½"	89 mm	R-15.2	RSI-2.7		
		□ 4"	102 mm	R-17.4	RSI-3.1		
		□ 1"	25 mm	R-4.3	RSI-0.8		
	4.25 pcf	□ 1½"	38 mm	R-6.5	RSI-1.1		
	68 kg/m³	□ 2"	51 mm	R-8.7	RSI-1.5		
		□ 2½"	64 mm	R-10.9	RSI-1.9		
	6.0 pcf 96 kg/m³	□ 1"	25 mm	R-4.5	RSI-0.8		
		□ 1½"	38 mm	R-6.8	RSI-1.2		
	- 0/	□ 2"	51 mm	R-9.1	RSI-1.6		